


Notes on Evaluating Sanding

Exercise 5.2



Add a coat of stain to your $\frac{1}{2}$ of each face of your panel – this will make any defects appear more readily.



Use an inspection light, or a light source from a low angle to view defects.

Grading

Mark your faces "A" and "B". Evaluate each based on the criteria below:

Face 1 ("A"): No apparent sand through (ghosting) of veneer	Face 1 ("A"): No Cross-Grain Scratches	Face 1 ("A"): Sanding marks are consistent and directional with the grain	Face 1 ("A"): No edge/end roll or dubbing	Face 1 ("A"): No pronounced Orbital Sanding Marks
